Vol. 03, Iss. 2 (2025) 164-185, DOI: 10.61552/JME.2025.02.002

JME

Journal of Materials and Engineering

www.jme.aspur.rs

Review article

A Critical Review of Current Corrosion Research

Shaimaa Al-Baghdadi[a], Ahmed A. Alamiery[a,*]

[a]*Energy and Renewable Energies Technology Center, University of Technology, Iraq, 10001, Iraq.*

Keywords:

Corrosion mechanisms
Materials science
Electrochemical processes
Environmental factors
Corrosion prevention

* Corresponding author:

Ahmed A. Alamiery
E-mail: dr.ahmed1975@gmail.com

Received: 4 May 2024
Revised: 16 June 2024
Accepted: 25 July 2024

A B S T R A C T

Corrosion, a pervasive phenomenon, poses significant challenges across various industries, impacting infrastructure, safety, and economic viability. This abstract aims to provide a succinct overview of the critical review of current corrosion research. It delves into the multifaceted nature of corrosion, highlighting its detrimental effects on materials and structures. The abstract outlines the methodologies employed in current corrosion research, emphasizing the interdisciplinary approaches necessary for comprehensive understanding and effective mitigation strategies. Furthermore, it discusses the emerging trends and innovations in corrosion science, including novel materials, advanced analytical techniques, and predictive modeling. The abstract concludes by underscoring the importance of ongoing research efforts in addressing corrosion-related issues and fostering sustainable technological advancements.

© 2025 Journal of Materials and Engineering

1. INTRODUCTION

Corrosion stands as a relentless adversary to the integrity and longevity of various materials, structures, and systems essential to human civilization. From the rusting of steel structures to the degradation of biomedical implants, corrosion manifests in diverse forms, constantly challenging our technological advancements and economic stability. In this critical review, we delve into the multifaceted realm of corrosion research, exploring its definitions, significance, and the scope of ongoing investigations [1-3]. Corrosion, in its essence, refers to the degradation of materials through chemical or electrochemical reactions with their environment [4,5]. This process often results in the gradual deterioration of the material's properties, leading to structural weakness, functional impairment, and, in severe cases, complete failure. The manifestations of corrosion span a wide spectrum, encompassing rust formation on iron and steel, pitting in aluminum alloys, tarnishing of metals, and the disintegration of polymers [6,7].

The mechanisms driving corrosion are as varied as the materials it affects. Some common corrosion processes include galvanic corrosion, where the presence of dissimilar metals in an electrolyte induces accelerated corrosion in one of the metals; uniform corrosion, characterized by relatively even material loss across the surface; localized corrosion, such as pitting and crevice corrosion, which occur at specific sites with increased corrosion susceptibility; and stress corrosion cracking, where the combination of tensile stress and a corrosive environment leads to crack propagation [8,9]. Understanding the intricacies of corrosion mechanisms is paramount for devising effective prevention and mitigation strategies. Without such comprehension, materials and structures are left vulnerable to degradation, compromising safety, reliability, and longevity [10,11]. Figure 1 illustrates the diverse manifestations of corrosion across different industries, highlighting its ubiquitous nature and far-reaching impacts on materials, structures, and systems essential to human civilization. Each sector faces unique corrosion challenges, necessitating tailored prevention and mitigation strategies to ensure the integrity and longevity of critical assets.

- **Infrastructure:** Corrosion poses a significant threat to infrastructure, including bridges, pipelines, buildings, and transportation systems. The rusting of steel structures, concrete degradation due to chloride-induced corrosion, and corrosion-induced fatigue in metallic components are among the common manifestations observed in this sector. The economic consequences of corrosion-related failures in infrastructure are substantial, leading to costly repairs, service disruptions, and compromised safety.
- **Energy:** In the energy sector, corrosion impacts various components of power generation, transmission, and distribution systems. Corrosion in pipelines, storage tanks, and offshore platforms can result in oil and gas leaks, environmental contamination, and operational downtime. Similarly, corrosion-related degradation in nuclear power plants and renewable energy systems can compromise safety and efficiency, highlighting the importance of corrosion-resistant materials and coatings.
- **Transportation:** Corrosion poses formidable challenges in the transportation sector, affecting vehicles, aircraft, ships, and railway infrastructure. The corrosion of automotive components, such as chassis, body panels, and exhaust systems, accelerates wear and compromises structural integrity, leading to safety hazards and reduced vehicle lifespan. Similarly, corrosion-induced fatigue in aircraft structures and marine vessels can jeopardize passenger safety and operational reliability, necessitating rigorous maintenance and corrosion prevention measures.
- **Healthcare:** In the healthcare industry, corrosion can have profound implications for biomedical devices and implants. The degradation of orthopedic implants, dental prosthetics, and surgical instruments due to corrosion can lead to implant failure, tissue inflammation, and patient discomfort. Moreover, corrosion-related release of metallic ions into the body can pose systemic health risks, underscoring the importance of biocompatible materials and corrosion-resistant coatings in medical device design.
- **Manufacturing:** Corrosion impacts various manufacturing processes and equipment, including metalworking, chemical processing, and electronics manufacturing. Corrosion-induced equipment failures, process contamination, and product defects can result in production delays, quality issues, and financial losses. Implementing corrosion-resistant materials, corrosion inhibitors, and corrosion monitoring techniques is crucial for ensuring operational reliability and product quality in manufacturing environments.

Overall, the figure emphasizes the need for interdisciplinary collaboration, innovative research, and proactive corrosion management practices across industries to address the pervasive challenges posed by corrosion and safeguard critical infrastructure, resources, and human health [12-15].



Fig. 1. Corrosion manifestations across various industries.

The importance of corrosion research cannot be overstated, considering its pervasive impact on virtually every sector of human activity. In infrastructure, corrosion poses a significant threat to the safety and functionality of bridges, pipelines, buildings, and transportation systems. The economic ramifications of corrosion-related failures are staggering, with billions of dollars lost annually due to repair, replacement, and downtime costs. In industries such as oil and gas, aerospace, automotive, and maritime, corrosion jeopardizes the integrity of critical components and equipment, endangering both personnel and assets. Furthermore, corrosion in biomedical devices and implants undermines patient safety and healthcare outcomes, necessitating continuous innovation in corrosion-resistant materials and coatings. Environmental considerations also underscore the importance of corrosion research. The release of toxic substances from corroded materials can pollute soil, water bodies, and the atmosphere, posing risks to ecosystems and human health. By developing sustainable corrosion prevention strategies and eco-friendly materials, researchers can mitigate these environmental hazards. Moreover, the evolution of modern technologies, such as renewable energy systems, electronic devices, and advanced manufacturing processes, demands materials with enhanced corrosion resistance and durability. Corrosion research plays a pivotal role in meeting these technological challenges and facilitating the transition to a more sustainable and resilient future [16-18].

This critical review encompasses a comprehensive examination of current trends, methodologies, challenges, and innovations in corrosion research. It encompasses a broad spectrum of disciplines, including materials science, chemistry, engineering, environmental science, and computational modeling. The review will elucidate fundamental corrosion mechanisms, explore state-of-the-art experimental and computational techniques, analyze case studies across various industries, and discuss emerging trends and future directions in corrosion science. Furthermore, the review will delve into the interdisciplinary nature of corrosion research, highlighting the synergistic collaborations between academia, industry, and government agencies. It will address the global dimensions of corrosion-related challenges, considering regional variations in environmental conditions, industrial practices, and regulatory frameworks. Ultimately, this review aims to provide valuable insights into the complex interplay between materials, environment, and corrosion processes, fostering dialogue and knowledge exchange among researchers, practitioners, and policymakers. By critically evaluating the current state of corrosion research, we endeavor to catalyze advancements in corrosion prevention, mitigation, and sustainable materials development, thereby mitigating the adverse impacts of corrosion on society, economy, and the environment [19,20].

While corrosion research has been a longstanding field of study, this review aims to bring fresh perspectives and insights by synthesizing the latest advancements and emerging trends in the discipline. By critically evaluating current research endeavors, methodologies, and challenges, this review seeks to identify novel approaches and innovative solutions for addressing corrosion-related issues across various industries and applications. Moreover, the review will highlight cutting-edge developments in materials science, nanotechnology, artificial intelligence, and other fields that are reshaping the landscape of corrosion research and paving the way for transformative advancements. The primary aim of this work is to provide a comprehensive and critical review of current corrosion research, encompassing a wide range of topics, methodologies, and applications. By

synthesizing existing literature and integrating diverse perspectives from academia, industry, and government agencies, this review seeks to enhance our understanding of corrosion mechanisms, prevention strategies, and mitigation techniques. Furthermore, the aim is to identify gaps in knowledge, highlight areas for further investigation, and propose avenues for future research directions. Ultimately, the goal is to facilitate knowledge exchange, foster collaboration, and catalyze advancements in corrosion science and technology. The objectives of this study can be summarized as follows [21-23]:

- **Evaluate Current Research Trends:** To analyze the latest developments and trends in corrosion research, including advancements in materials science, electrochemistry, surface engineering, and environmental monitoring.
- **Assess Methodologies and Techniques:** To critically evaluate experimental, computational, and analytical techniques employed in corrosion research, identifying strengths, limitations, and emerging approaches.
- **Explore Interdisciplinary Perspectives**: To examine the interdisciplinary nature of corrosion research, encompassing contributions from materials science, chemistry, engineering, environmental science, and other fields.
- **Identify Challenges and Limitations:** To identify key challenges and limitations in corrosion prevention, detection, and mitigation, including issues related to corrosion monitoring, predictive modeling, and sustainable materials development.
- **Highlight Emerging Trends and Innovations:** To showcase cutting-edge developments and innovations in corrosion science and technology, such as advanced materials, nanotechnology applications, and machine learning-based predictive modeling.
- **Discuss Case Studies and Applications:** To analyze real-world case studies and applications of corrosion research across various industries, including infrastructure, energy, transportation, healthcare, and manufacturing.
- **Propose Future Directions and Recommendations:** To propose recommendations for future research directions, collaboration initiatives, policy interventions, and regulatory frameworks aimed at advancing corrosion science and mitigating its societal, economic, and environmental impacts.

2. FUNDAMENTALS OF CORROSION

Corrosion, an electrochemical process, represents the gradual degradation of materials due to reactions with their surrounding environment. Understanding the fundamentals of corrosion is crucial for developing effective prevention and mitigation strategies across various industries and applications. This section delves into the chemical processes involved in corrosion, the different mechanisms of corrosion, and the factors influencing corrosion susceptibility [24,25].

2.1 Chemical Processes Involved

Corrosion typically involves electrochemical reactions between a metal, an electrolyte, and other environmental factors. The basic components of a corrosion cell include an anode (where oxidation occurs), a cathode (where reduction occurs), an electrolyte (which facilitates ion transport), and an external circuit (which allows electron flow). At the anode, metal atoms lose electrons and enter the electrolyte as positively charged ions, a process known as oxidation. For example, in the corrosion of iron (Fe) to form iron ions (Fe^{2+}) [26,27]:

$$Fe \rightarrow Fe^{2+} + 2e^-$$

At the cathode, reduction reactions take place, often involving the reduction of oxygen or hydrogen ions. For instance, in the reduction of oxygen to form hydroxide ions:

$$1/2\ O_2 + H_2O + 2e^- \rightarrow 2\ OH^-$$

The overall corrosion process involves the continuous transfer of electrons from the anode to the cathode, resulting in the deterioration of the metal [28-30].

2.2 Types of Corrosion Mechanisms

Corrosion can manifest in various forms, depending on the specific environmental conditions, materials involved, and electrochemical processes at play. Some common types of corrosion mechanisms include [31-33]:

- **Uniform Corrosion:** Uniform corrosion occurs when the entire surface of a metal undergoes relatively uniform corrosion, leading to a gradual loss of material thickness. This type of corrosion is often influenced by factors such as temperature, humidity, and the chemical composition of the electrolyte.
- **Localized Corrosion:** Localized corrosion refers to corrosion that occurs at specific sites on the metal surface, resulting in localized damage such as pitting, crevice corrosion, or galvanic corrosion. These forms of corrosion are often initiated by local variations in environmental conditions or surface properties.
- **Pitting Corrosion**: Pitting corrosion involves the formation of small pits or cavities on the metal surface, typically in the presence of aggressive ions or localized defects. Pitting corrosion can lead to rapid metal deterioration and is particularly challenging to detect and mitigate.
- **Crevice Corrosion:** Crevice corrosion occurs in narrow gaps or crevices between two surfaces, where stagnant electrolyte conditions promote localized corrosion. Crevice corrosion is common in areas with poor fluid circulation, such as bolted joints, gaskets, and under-deposit corrosion.
- **Galvanic Corrosion:** Galvanic corrosion occurs when two dissimilar metals are in contact in the presence of an electrolyte, leading to accelerated corrosion of the less noble (more reactive) metal. Galvanic corrosion can occur in various engineering applications, such as plumbing systems, marine environments, and electrical connections.
- **Intergranular Corrosion:** Intergranular corrosion occurs along the grain boundaries of a metal, typically due to preferential dissolution of the grain boundary regions. This type of corrosion can result from metallurgical impurities, thermal treatments, or sensitization processes.

2.3 Factors Influencing Corrosion

Several factors influence the susceptibility of materials to corrosion, including [34-36]:

- **Environmental Conditions:** Environmental factors such as temperature, humidity, pH, salinity, and atmospheric pollutants can significantly impact corrosion rates. For example, high temperatures and humidity levels can accelerate corrosion reactions, while acidic or alkaline environments can promote or inhibit corrosion, depending on the material properties.
- **Material Properties:** The chemical composition, microstructure, and mechanical properties of materials play a critical role in their corrosion resistance. Materials with passive oxide layers, such as stainless steels and aluminum alloys, exhibit enhanced corrosion resistance compared to pure metals or alloys lacking protective coatings.
- **Electrochemical Potential:** The electrochemical potential of a material, determined by its position in the galvanic series, influences its tendency to corrode relative to other materials in the same electrolyte. Materials with more negative (less noble) potentials are more susceptible to corrosion in galvanic coupling scenarios.
- **Flow Conditions:** Fluid flow patterns and velocities can affect corrosion rates by influencing mass transport and fluid-surface interactions. Turbulent flow regimes may promote corrosion by removing protective surface films or increasing mass transfer rates, whereas laminar flow conditions may inhibit corrosion by maintaining a stable boundary layer.
- **Mechanical Stress:** Mechanical stresses, such as tensile, compressive, or cyclic loading, can exacerbate corrosion by inducing localized deformation, cracking, or surface defects. Stress corrosion cracking (SCC) is a particularly insidious form of corrosion that occurs under combined mechanical and corrosive environments.
- **Presence of Contaminants**: The presence of contaminants, such as chlorides, sulfides,

oxygen, or microbial species, can accelerate corrosion processes by promoting aggressive chemical reactions or microbial-induced corrosion mechanisms. Contaminants may originate from industrial processes, environmental pollutants, or biological sources.

Understanding these factors is essential for predicting and mitigating corrosion risks in practical applications, enabling the development of tailored corrosion prevention strategies and materials selection criteria. By addressing the underlying mechanisms and controlling the influencing factors, engineers and scientists can effectively manage corrosion-related challenges and extend the service life of critical assets and infrastructure [37,38]. Figure 2 illustrates various types of corrosion mechanisms encountered in engineering and industrial applications, each characterized by distinct patterns of material degradation and environmental influences. Understanding these corrosion mechanisms is essential for implementing effective prevention and mitigation strategies tailored to specific conditions and materials [39-41].




Fig. 2 Types of Corrosion Mechanisms.

Table 1 highlights the various factors that influence corrosion processes in materials. Environmental factors such as temperature and humidity play a significant role in accelerating corrosion rates, especially in harsh conditions like marine environments with high chloride concentrations. Material properties, including composition and microstructure, determine susceptibility to corrosion, with alloying elements often enhancing resistance. Electrochemical factors such as pH and oxygen concentration influence corrosion kinetics, while mechanical factors like stress and strain can induce localized corrosion, such as stress corrosion cracking in pipelines.

Table 1. Factors Influencing Corrosion.

Factor	Influence	Examples
Environmental	Chemical composition, temperature, humidity	High chloride concentration in marine environments
Material	Composition, microstructure, surface condition	Alloying elements in stainless steel
Electrochemical	Electrolyte conductivity, pH, oxygen concentration	Acidic environments promoting corrosion
Mechanical	Stress, strain, fatigue	Stress corrosion cracking in pipelines

3. METHODOLOGIES IN CORROSION RESEARCH

Corrosion research encompasses a wide range of methodologies, from experimental techniques and computational modeling to field studies and case analyses. These methodologies play a crucial role in advancing our understanding of corrosion mechanisms, developing effective prevention strategies, and mitigating corrosion-related risks in various industries and applications. This section explores the key methodologies employed in corrosion research and their contributions to the field [42-44]. Corrosion research employs a diverse array of methodologies, encompassing experimental techniques, computational approaches, and field studies, each offering unique insights into corrosion mechanisms, material behavior, and corrosion management strategies. Figure 3 illustrates the key methodologies employed in corrosion research and their contributions to advancing our understanding of corrosion processes and developing effective corrosion prevention and mitigation strategies [43-45].



Fig. 3 Methodologies in Corrosion Research.

3.1 Experimental Techniques

Experimental techniques form the cornerstone of corrosion research, allowing researchers to investigate the behavior of materials in different environments and under varying conditions. Some commonly used experimental techniques in corrosion research include [46-48]:

- **Electrochemical Methods**: Electrochemical techniques, such as potentiodynamic polarization, electrochemical impedance spectroscopy (EIS), and cyclic voltammetry, are widely used to study corrosion kinetics, corrosion rates, and electrochemical parameters of materials. These techniques provide valuable insights into the corrosion mechanisms and electrochemical behavior of metals and alloys.
- **Surface Analysis Techniques:** Surface analysis techniques, including scanning electron microscopy (SEM), atomic force microscopy (AFM), X-ray photoelectron spectroscopy (XPS), and energy-dispersive X-ray spectroscopy (EDS), are employed to examine the morphology, composition, and structure of corroded surfaces. These techniques help identify corrosion products, surface defects, and microstructural changes induced by corrosion processes.
- **Corrosion Testing:** Corrosion testing involves exposing materials to simulated or real-world corrosive environments and monitoring their degradation over time. Common corrosion testing methods include salt spray testing, immersion testing, accelerated corrosion testing, and electrochemical corrosion testing. These tests provide valuable data on corrosion resistance, corrosion mechanisms, and material performance under specific conditions.
- **Mechanical Testing:** Mechanical testing techniques, such as tensile testing, hardness testing, and fatigue testing, are used to evaluate the mechanical properties and integrity of materials before and after corrosion exposure. These tests help assess the effects of corrosion on material strength, ductility, and fracture behavior, providing insights into corrosion-induced mechanical failures.
- **Microbiologically Influenced Corrosion (MIC) Studies:** MIC studies involve culturing microorganisms in corrosive environments and assessing their role in promoting or mitigating corrosion. Microbiological techniques, such as microbial culture assays, molecular biology techniques (e.g., polymerase chain reaction, DNA sequencing), and biofilm analysis, are used to characterize microbial communities and their interactions with metals and alloys.

Experimental techniques play a vital role in elucidating corrosion mechanisms, evaluating material performance, and validating theoretical models. By combining various experimental approaches, researchers can gain a comprehensive understanding of corrosion processes and develop effective corrosion prevention and mitigation strategies [49-51].

3.2 Computational Approaches

Computational approaches have emerged as powerful tools in corrosion research, enabling researchers to simulate corrosion processes, predict material behavior, and optimize corrosion-resistant designs. Computational methods complement experimental techniques by providing insights into complex corrosion phenomena that are challenging to observe or quantify experimentally. Some commonly used computational approaches in corrosion research include [52-57]:

- **Molecular Dynamics (MD) Simulations:** MD simulations model the atomic-scale interactions between materials and their environment, allowing researchers to study corrosion mechanisms at the molecular level. MD simulations provide insights into processes such as ion transport, adsorption, and surface reactions, facilitating the design of corrosion-resistant materials and coatings.
- **Density Functional Theory (DFT):** DFT calculations predict the electronic structure and properties of materials, enabling researchers to investigate the thermodynamics and kinetics of corrosion reactions. DFT calculations provide valuable information on the stability of corrosion products, the adsorption of corrosive species, and the activation barriers of corrosion processes.
- **Finite Element Analysis (FEA):** FEA models the mechanical and electrochemical behavior of materials subjected to corrosion and mechanical loading. FEA simulations help predict stress corrosion cracking, corrosion-induced deformation, and material degradation under complex loading conditions, aiding in the design of corrosion-resistant structures and components.
- **Computational Fluid Dynamics (CFD):** CFD simulations model fluid flow and mass transport in corrosive environments, providing insights into corrosion rates, corrosion product deposition, and fluid-solid interactions. CFD simulations help optimize fluid flow patterns, mitigate corrosion hotspots, and design corrosion-resistant equipment and piping systems.
- **Machine Learning (ML) and Data-driven Approaches:** ML algorithms analyze large datasets of experimental and computational results to identify correlations, patterns, and predictive models of corrosion behavior. ML techniques, such as neural networks, support vector machines, and random forests, aid in corrosion prediction, materials screening, and optimization of corrosion-resistant coatings.

Computational approaches offer valuable insights into corrosion mechanisms, materials behavior, and performance under diverse conditions. By integrating computational modeling with experimental validation, researchers can accelerate the development of corrosion-resistant materials, coatings, and engineering solutions [58-62].

3.3 Field Studies and Case Analyses

Field studies and case analyses provide valuable real-world insights into corrosion phenomena, material performance, and corrosion management practices. Field studies involve monitoring corrosion behavior in operational environments, assessing corrosion damage in existing structures, and implementing corrosion control measures in industrial settings. Case analyses examine past corrosion failures, incidents, or accidents to identify root causes, lessons learned, and best practices for corrosion prevention and mitigation. Some key aspects of field studies and case analyses in corrosion research include [63-67]:

- **Corrosion Monitoring and Inspection:** Field studies involve deploying corrosion monitoring devices, sensors, and probes to assess corrosion rates, corrosion mechanisms, and environmental conditions in situ. Non-destructive testing (NDT) techniques, such as ultrasonic testing, eddy current testing, and radiographic testing, are used to inspect structures for corrosion damage without causing disruption to operations.
- **Material Performance Evaluation**: Field studies evaluate the performance of corrosion-resistant materials, coatings, and corrosion inhibitors in real-world environments. Long-term exposure tests, service life assessments, and material characterization studies provide valuable data on material degradation mechanisms, durability, and suitability for specific applications.
- **Failure Analysis and Root Cause Investigation:** Case analyses involve investigating corrosion failures, identifying root causes, and implementing corrective actions to prevent recurrence. Failure analysis techniques, such as metallurgical analysis, fractography, and chemical analysis, help determine the factors contributing to corrosion failures, including material defects, design flaws, operational errors, and environmental factors.

- **Corrosion Management Strategies:** Field studies and case analyses inform the development of corrosion management strategies tailored to specific industries, applications, and operating conditions. Corrosion management plans, corrosion risk assessments, and asset integrity management programs aim to identify, prioritize, and mitigate corrosion risks through preventive maintenance, corrosion control measures, and asset monitoring.

Field studies and case analyses provide valuable insights into the practical challenges and solutions for corrosion prevention and mitigation in diverse industrial sectors [68-72]. By documenting real-world experiences and lessons learned, researchers and practitioners can improve corrosion management practices, enhance infrastructure resilience, and optimize resource allocation for corrosion control efforts.

In conclusion, methodologies in corrosion research encompass a diverse array of experimental, computational, and field-based approaches, each offering unique advantages and insights into corrosion mechanisms, material behavior, and corrosion management strategies. By integrating these methodologies and fostering interdisciplinary collaboration, researchers can advance our understanding of corrosion processes, develop innovative solutions for corrosion prevention and mitigation, and ensure the integrity and longevity of critical assets and infrastructure

4. INTERDISCIPLINARY PERSPECTIVES IN CORROSION RESEARCH

Corrosion research benefits from interdisciplinary perspectives, drawing insights from fields such as materials science and engineering, electrochemistry, surface science, and environmental science. This multidisciplinary approach allows researchers to address the complex interactions between materials, environment, and corrosion processes, leading to innovative solutions for corrosion prevention, mitigation, and materials design. This section explores the contributions of each discipline to corrosion research and their role in advancing our understanding of corrosion mechanisms and developing effective corrosion management strategies [73-77].

4.1 Materials Science and Engineering

Materials science and engineering play a central role in corrosion research, focusing on the development of corrosion-resistant materials, coatings, and surface treatments. Materials scientists study the structure, properties, and performance of materials under corrosive conditions, aiming to enhance their durability, reliability, and longevity. Key contributions of materials science and engineering to corrosion research include [78-82]:

- **Material Selection and Design**: Materials scientists select and design materials with intrinsic corrosion resistance or develop corrosion-resistant alloys, composites, and coatings tailored to specific applications and environments. By understanding the microstructure-property relationships of materials, researchers can optimize their corrosion resistance while maintaining mechanical, thermal, and functional properties [83,84].
- **Corrosion Mechanisms**: Materials scientists investigate the mechanisms of corrosion at the atomic and microstructural levels, elucidating the factors influencing corrosion susceptibility, such as grain boundaries, defects, and alloying elements. By studying corrosion mechanisms, researchers can develop predictive models and design strategies to mitigate corrosion-induced degradation. Table 2 outlines some of the most common corrosion mechanisms encountered in engineering materials. Uniform corrosion, characterized by a consistent loss of material over the entire surface, is often observed in atmospheric conditions. Pitting corrosion, on the other hand, leads to the formation of localized pits or craters, significantly affecting the material's integrity. Galvanic corrosion occurs when two dissimilar metals are in contact, leading to accelerated corrosion of the less noble metal. Understanding these mechanisms is crucial for implementing targeted prevention and mitigation strategies [85-87].
- **Surface Modification Techniques**: Materials scientists develop surface modification techniques, such as passivation, anodization, chemical vapor deposition (CVD), and physical vapor deposition (PVD), to enhance the corrosion resistance of materials. Surface

treatments modify the chemical composition, morphology, and surface energy of materials, creating protective barriers against corrosive attack [88,89].

- **Advanced Characterization Methods**: Materials scientists employ advanced characterization techniques, such as scanning electron microscopy (SEM), transmission electron microscopy (TEM), X-ray diffraction (XRD), and atomic force microscopy (AFM), to analyze the morphology, composition, and structure of corroded surfaces. These techniques provide insights into corrosion products, localized corrosion phenomena, and surface defects, guiding materials design and corrosion prevention strategies [90-92].

Table 2. Common Corrosion Mechanisms.

Mechanism	Description	Examples	Contributing Factors
Uniform Corrosion	Gradual loss of material thickness over the entire surface	Rusting of steel structures, atmospheric corrosion	- Presence of moisture and oxygen - Acidic or alkaline environments - High operating temperatures
Pitting Corrosion	Formation of localized pits or craters on the surface	Pitting corrosion of stainless steel, aluminum	- Halide ions (chlorides) - Localized acidic environments - Crevices or imperfections on the surface
Galvanic Corrosion	Accelerated corrosion due to electrochemical coupling	Corrosion of metal fasteners in contact with dissimilar metals	- Significant difference in electrode potentials between metals - Electrolyte presence (e.g., saltwater) - Large surface area ratio of active to noble metal
Crevice Corrosion	Localized attack at occluded areas where stagnant conditions and concentration of corrosive species can occur	Corrosion beneath gaskets or deposits on metal surfaces	- Limited oxygen supply and buildup of aggressive ions within crevices - Stagnant or slow-moving electrolytes
Intergranular Corrosion	Preferential attack at grain boundaries within a metal microstructure	Corrosion of sensitized stainless steel (improper heat treatment)	- Chromium depletion at grain boundaries - Specific microstructures and sensitization of alloys
Stress Corrosion Cracking (SCC)	Brittle failure due to the combined effects of tensile stress and a corrosive environment	Cracking of brass cartridge cases, stainless steel piping in high-temperature chloride environments-	Susceptible material properties (e.g., some alloys) - Residual or applied tensile stresses - Specific corrosive media

4.2 Electrochemistry

Electrochemistry provides fundamental insights into the electrochemical processes underlying corrosion phenomena, facilitating the quantitative analysis of corrosion kinetics, corrosion rates, and electrochemical parameters. Electrochemical techniques are widely used to study corrosion behavior, characterize corrosion mechanisms, and evaluate the effectiveness of corrosion inhibitors and protective coatings. Key contributions of electrochemistry to corrosion research include [93-96]:

- **Corrosion Kinetics:** Electrochemical methods, such as potentiodynamic polarization, electrochemical impedance spectroscopy (EIS), and cyclic voltammetry, are used to measure corrosion kinetics, polarization curves, and electrochemical parameters of materials. These techniques provide information on corrosion rates, corrosion potentials, and corrosion mechanisms, aiding in the assessment of material performance and corrosion resistance.
- **Passivity and Film Formation:** Electrochemical studies elucidate the mechanisms of passivation and film formation on metal surfaces, identifying the factors influencing the stability and protective properties of passive films. Understanding passivation processes is critical for designing corrosion-resistant materials and optimizing surface treatments to enhance passivity.

- **Corrosion Inhibition:** Electrochemical techniques assess the effectiveness of corrosion inhibitors and surface treatments in mitigating corrosion. By monitoring changes in corrosion current, polarization resistance, and electrochemical impedance, researchers evaluate the adsorption, inhibition efficiency, and mode of action of corrosion inhibitors, guiding their selection and optimization for practical applications.
- **Localized Corrosion Mechanisms:** Electrochemical studies investigate localized corrosion phenomena, such as pitting corrosion, crevice corrosion, and stress corrosion cracking, by mapping local variations in electrochemical activity and corrosion susceptibility. These studies provide insights into the initiation, propagation, and mitigation of localized corrosion, informing materials design and corrosion control strategies.

4.3 Surface Science

Surface science focuses on the characterization, manipulation, and control of material surfaces and interfaces, providing insights into surface reactions, adsorption phenomena, and surface-mediated processes relevant to corrosion research. Surface science techniques are used to study surface morphology, chemistry, and reactivity, enabling researchers to understand the interactions between materials and corrosive environments. Key contributions of surface science to corrosion research include [97-102]:

- **Surface Analysis Techniques:** Surface science techniques, such as X-ray photoelectron spectroscopy (XPS), Auger electron spectroscopy (AES), secondary ion mass spectrometry (SIMS), and scanning probe microscopy (SPM), are employed to analyze the composition, structure, and properties of surfaces and interfaces. These techniques provide detailed information on surface chemistry, corrosion products, and adsorbed species, aiding in the characterization of corroded surfaces and the identification of surface reactions.
- **Adsorption and Passivation:** Surface science studies investigate the adsorption of corrosive species, inhibitors, and passivating agents on metal surfaces, elucidating the mechanisms of surface passivation, film formation, and corrosion inhibition. By probing the interactions between adsorbates and surfaces, researchers design effective inhibitors and surface treatments to prevent corrosion and protect materials from degradation.
- **Surface Modification and Functionalization:** Surface science techniques enable the modification and functionalization of material surfaces to enhance their corrosion resistance and performance. Surface treatments, such as plasma etching, ion implantation, and self-assembled monolayers (SAMs), modify surface chemistry, wettability, and adhesion properties, creating barriers against corrosive attack and improving material durability.
- **Corrosion Kinetics at Interfaces:** Surface science studies investigate the kinetics of corrosion reactions at interfaces, including metal-electrolyte interfaces, metal-oxide interfaces, and metal-polymer interfaces. By quantifying reaction rates, activation energies, and interfacial processes, researchers elucidate the mechanisms of corrosion initiation, propagation, and inhibition at the nanoscale, guiding the design of corrosion-resistant materials and coatings.

4.4 Environmental Science

Environmental science examines the interactions between natural and anthropogenic factors and their impact on ecosystems, climate, and environmental quality. In the context of corrosion research, environmental science provides insights into the effects of environmental conditions, pollutants, and climate change on corrosion processes and material degradation. Key contributions of environmental science to corrosion research include [103-106]:

- **Corrosive Environments:** Environmental science studies characterize corrosive environments, such as marine environments, industrial atmospheres, and polluted waters, assessing their chemical composition, temperature, humidity, and exposure conditions. By understanding the corrosive

agents and mechanisms prevalent in different environments, researchers develop strategies to mitigate corrosion risks and protect infrastructure.

- **Atmospheric Corrosion:** Environmental science investigates atmospheric pollutants, such as sulfur dioxide (SO2), nitrogen oxides (NOx), ozone (O3), and particulate matter, and their role in atmospheric corrosion processes. By monitoring air quality and studying corrosion rates on outdoor surfaces, researchers assess the impact of air pollution on materials degradation and urban infrastructure.
- **Water Chemistry and Corrosion:** Environmental science examines water chemistry, pH, alkalinity, conductivity, and dissolved ions (e.g., chlorides, sulfates, carbonates) in natural and industrial waters, evaluating their corrosivity and potential for inducing corrosion in metals and alloys. By analyzing water quality parameters, researchers assess the risk of localized corrosion, microbiologically influenced corrosion (MIC), and corrosion-related water contamination.
- **Climate Change and Corrosion:** Environmental science investigates the effects of climate change, including temperature fluctuations, extreme weather events, and sea level rise, on corrosion processes and infrastructure resilience. By modeling climate projections and assessing vulnerability to corrosion-induced damage, researchers develop adaptation strategies and sustainable infrastructure designs to mitigate the impacts of climate change on corrosion.

Interdisciplinary perspectives in corrosion research integrate insights from materials science, electrochemistry, surface science, and environmental science, enabling researchers to address the complex interactions between materials, environment, and corrosion processes. By fostering collaboration across disciplines, researchers develop holistic approaches to corrosion prevention, mitigation, and materials design, ensuring the integrity and sustainability of critical infrastructure and technological systems in diverse applications and environments [107-109].

5. CHALLENGES AND LIMITATIONS IN CORROSION RESEARCH

Corrosion research faces numerous challenges and limitations, ranging from technical constraints to economic and environmental considerations. Overcoming these challenges is essential for advancing corrosion science, developing effective prevention strategies, and mitigating the economic and environmental impacts of corrosion. This section explores some of the key challenges and limitations in corrosion research and their implications for corrosion monitoring, prevention, and control, as well as the economic and environmental impacts of corrosion [110-112].

5.1 Corrosion Monitoring and Detection

- **Limited Sensitivity and Resolution**: Traditional corrosion monitoring techniques may lack sensitivity and resolution for detecting early-stage corrosion or localized corrosion phenomena. Improving detection limits and spatial resolution is essential for identifying corrosion hotspots and initiating timely corrective actions.
- **Complexity of Real-World Environments:** Corrosion monitoring in real-world environments, such as marine, industrial, and aerospace settings, poses challenges due to the complexity of environmental conditions, including temperature fluctuations, fluid flow dynamics, and chemical variability. Developing robust monitoring systems capable of operating in harsh environments is crucial for accurate corrosion assessment.
- **Cost and Accessibility:** Advanced corrosion monitoring technologies, such as remote sensing, wireless sensor networks, and corrosion sensors, may be costly to implement and maintain, limiting their widespread adoption, particularly in resource-constrained industries and infrastructure sectors. Addressing cost barriers and improving accessibility to corrosion monitoring tools is essential for maximizing corrosion control efforts [113-115].

5.2 Corrosion Prevention and Control

Table 3 outlines various corrosion prevention strategies employed to mitigate material degradation. Protective coatings act as a barrier

between the material and corrosive environment, preventing direct contact and reducing corrosion rates. Cathodic protection systems, such as sacrificial anodes or impressed current systems, provide an electrochemical shield to inhibit corrosion. Material selection plays a crucial role, with the use of corrosion-resistant materials or alloys tailored to specific applications, such as stainless steel in marine environments. Implementing these strategies effectively can significantly extend the lifespan of materials and infrastructure [116-118].

Table 3. Corrosion Prevention Strategies.

Strategy	Description	Examples
Protective Coatings	Barrier between material and corrosive environment	Paint coatings on metal surfaces
Cathodic Protection	Sacrificial anode or impressed current systems	Galvanic cathodic protection in buried pipelines
Material Selection	Corrosion-resistant materials or alloys	Stainless steel for marine applications

- **Multifaceted Nature of Corrosion:** Corrosion is a multifaceted phenomenon influenced by various factors, including material properties, environmental conditions, and operational parameters. Developing comprehensive corrosion prevention strategies requires integrating diverse approaches, such as materials selection, design optimization, surface treatments, and corrosion inhibitors.
- **Effectiveness of Preventive Measures:** The effectiveness of corrosion prevention measures, such as protective coatings, inhibitors, and cathodic protection systems, may vary depending on the specific application, environmental conditions, and operational requirements. Continuous monitoring and evaluation of preventive measures are necessary to ensure long-term corrosion protection and performance.
- **Compatibility and Interactions:** Corrosion prevention methods must be compatible with other system components and materials to avoid adverse interactions or unintended consequences. Compatibility issues may arise from differences in material properties, chemical compatibility, or electrochemical interactions, requiring careful selection and integration of corrosion control measures.

5.3 Economic and Environmental Impacts

- **Cost of Corrosion:** Corrosion imposes significant economic costs on industries, governments, and society as a whole, including repair and replacement expenses, downtime and productivity losses, environmental remediation costs, and infrastructure degradation. Quantifying the economic impact of corrosion and implementing cost-effective corrosion management strategies is essential for minimizing financial losses and maximizing resource efficiency.
- **Environmental Degradation:** Corrosion-related environmental impacts, such as metal leaching, soil and water contamination, and ecosystem disruption, pose environmental risks and sustainability challenges. Addressing the environmental consequences of corrosion requires implementing pollution prevention measures, adopting environmentally friendly materials and coatings, and promoting sustainable corrosion management practices.
- **Resource Consumption and Waste Generation:** Corrosion-related maintenance, repair, and replacement activities consume natural resources and generate waste streams, contributing to resource depletion and environmental pollution. Implementing corrosion prevention and control measures that minimize resource consumption, waste generation, and environmental footprint is critical for sustainable development and responsible resource management.
- **Health and Safety Risks:** Corrosion-induced failures and accidents pose risks to human health and safety, particularly in critical infrastructure, transportation systems, and industrial facilities. Preventing corrosion-related incidents requires implementing robust safety protocols, conducting risk assessments, and prioritizing corrosion control measures that mitigate potential hazards and protect public health .

Addressing the challenges and limitations in corrosion research requires collaborative efforts among researchers, engineers, policymakers, and stakeholders to develop innovative solutions, implement best practices,

and promote sustainable corrosion management strategies. By advancing our understanding of corrosion processes, enhancing monitoring and detection capabilities, improving prevention and control measures, and mitigating the economic and environmental impacts of corrosion, we can safeguard critical infrastructure, protect natural resources, and promote sustainable development for future generations [119-120].

6. FUTURE DIRECTIONS AND RECOMMENDATIONS

As corrosion continues to pose significant challenges across various industries, future research efforts should focus on innovative solutions, interdisciplinary collaborations, and policy interventions to address these challenges effectively. Bridging the gap between research and industry, fostering collaborative initiatives, and implementing robust regulatory frameworks are essential for advancing corrosion science and mitigating its economic and environmental impacts.

6.1 Bridging the Gap between Research and Industry

- **Technology Transfer and Commercialization:** Facilitating the transfer of corrosion research findings and technologies from academia to industry is critical for translating scientific discoveries into practical applications. Establishing technology transfer offices, incubators, and industry-academic partnerships can accelerate the commercialization of corrosion-resistant materials, coatings, and corrosion monitoring technologies.
- **Industry Engagement and Stakeholder Collaboration:** Engaging industry stakeholders, including manufacturers, engineers, asset managers, and regulatory agencies, in collaborative research projects fosters knowledge exchange, identifies industry needs, and validates research outcomes in real-world settings. Industry-academic consortia, joint research programs, and technology roadmapping initiatives promote synergistic collaborations and mutual benefits for academia and industry.

6.2 Collaborative Initiatives and Knowledge Exchange

- **Interdisciplinary Research Consortia:** Establishing interdisciplinary research consortia and centers of excellence dedicated to corrosion science promotes collaboration among materials scientists, chemists, engineers, and environmental scientists. These consortia facilitate interdisciplinary research, share resources and expertise, and address complex corrosion challenges through collaborative projects and joint funding opportunities.
- **Knowledge Exchange Platforms:** Developing knowledge exchange platforms, such as conferences, workshops, webinars, and online forums, fosters communication, networking, and dissemination of best practices in corrosion research and technology. These platforms provide opportunities for researchers, practitioners, policymakers, and industry stakeholders to share insights, showcase innovations, and build partnerships for collaborative research and technology transfer.

6.3 Policy Implications and Regulatory Frameworks

- **Standardization and Certification**: Developing international standards, guidelines, and certification programs for corrosion prevention, testing, and materials selection ensures consistency, reliability, and quality assurance in corrosion control practices. Regulatory agencies, industry associations, and standards organizations collaborate to establish best practices and regulatory frameworks that promote safe, sustainable, and cost-effective corrosion management.
- **Incentive Mechanisms and Funding Support:** Providing incentives, grants, and funding support for corrosion research and development encourages investments in innovative technologies, infrastructure upgrades, and corrosion mitigation strategies. Public-private partnerships, research grants, and tax incentives incentivize industry participation and accelerate the adoption of corrosion-resistant materials and technologies.

7. CONCLUSION

In conclusion, corrosion science plays a crucial role in addressing the economic, environmental, and societal challenges posed by corrosion. By bridging the gap between research and industry, fostering collaborative initiatives, and implementing robust regulatory frameworks, we can advance corrosion science, promote technology transfer, and mitigate the economic and environmental impacts of corrosion. Sustained research efforts, interdisciplinary collaborations, and policy interventions are essential for safeguarding critical infrastructure, protecting natural resources, and ensuring sustainable development in the face of corrosion challenges.

7.1 Summary of Key Findings

- Corrosion poses significant economic, environmental, and safety risks across various industries and sectors.
- Bridging the gap between research and industry is essential for translating scientific discoveries into practical applications and technologies.
- Collaborative initiatives and knowledge exchange platforms facilitate interdisciplinary research, technology transfer, and best practices dissemination in corrosion science.
- Policy implications and regulatory frameworks promote standardization, certification, and funding support for corrosion research, development, and implementation.
- Sustained research efforts and continued investments in corrosion science are crucial for addressing emerging challenges and advancing sustainable corrosion management practices.

7.2 Importance of Sustained Research Efforts

Sustained research efforts in corrosion science are essential for:

- Developing innovative solutions to corrosion challenges.
- Advancing materials science, electrochemistry, and surface science for corrosion prevention and control.
- Promoting interdisciplinary collaborations and knowledge exchange.
- Informing policy decisions and regulatory frameworks for sustainable corrosion management.
- Enhancing industry competitiveness, resilience, and environmental stewardship.

7.3 Outlook for Advancements in Corrosion Science

The outlook for advancements in corrosion science is promising, with opportunities for:

- Developing next-generation corrosion-resistant materials and coatings.
- Integrating advanced monitoring technologies and predictive modeling tools.
- Implementing holistic corrosion management strategies and risk-based approaches.
- Enhancing sustainability, resilience, and safety in infrastructure and industrial systems.
- Leveraging emerging technologies, such as nanotechnology, biotechnology, and artificial intelligence, for corrosion research and innovation.

REFERENCES

[1] B. S. Mahdi *et al.*, “Corrosion inhibition of mild steel in hydrochloric acid environment using terephthaldehyde based on Schiff base: gravimetric, thermodynamic, and computational studies,” *Molecules*, vol. 27, no. 15, p. 4857, Jul. 2022, doi: 10.3390/molecules27154857

[2] Q. Jawad, D. Zinad, R.D. Salim, A.A. Al-Amiery, T.S. Gaaz, M.S. Takriff and A. Kadhum, "Synthesis, Characterization, and Corrosion Inhibition Potential of Novel Thiosemicarbazone on Mild Steel in Sulfuric Acid Environment," *Coatings*, 2019, 9, 729. doi: 10.3390/coatings9110729

[3] S. Al-Baghdadi, F. Noori, W.K. Ahmed and A.A. Al-Amiery, "Thiadiazole as a potential corrosion inhibitor for mild steel in 1 M HCl," *J. Adv. Electrochem.*, 2016, 2, 67–69.

[4] A.M. Resen, M. Hanoon, R.D. Salim, A.A. Al-Amiery, L.M. Shaker and A.A.H. Kadhum, "Gravimetrical, theoretical, and surface morphological investigations of corrosion

inhibition effect of 4-(benzoimidazole-2-yl) pyridine on mild steel in hydrochloric acid," *Koroze Ochr. Mater.*, 2020, 64, 122–130. doi: 10.2478/kom-2020-0018

[5] S. Junaedi, A. Al-Amiery, A. Kadihum, A. Kadhum and A. Mohamad, "Inhibition effects of a synthesized novel 4-aminoantipyrine derivative on the corrosion of mild steel in hydrochloric acid solution together with quantum chemical studies," *Int. J. Mol. Sci.*, 2013, 14, 11915–11928. doi: 10.3390/ijms140611915

[6] M.M. Solomon, I.E. Uzoma, J.A.O. Olugbuyiro and O.T. Ademosun, "A Censorious Appraisal of the Oil Well Acidizing Corrosion Inhibitors," *J. Pet. Sci. Eng.*, 2022, 215, 110711. doi: 10.1016/j.petrol.2022.110711

[7] D. Wang, Y. Li, B. Chen and L. Zhang, "Novel Surfactants as Green Corrosion Inhibitors for Mild Steel in 15% HCl: Experimental and Theoretical Studies," *Chem. Eng. J.*, 2020, 402, 126219. doi: 10.1016/j.cej.2020.126219

[8] B. El-Haitout, I. Selatnia, H. Lgaz, M.R. Al-Hadeethi, H.-S. Lee, A. Chaouiki, Y.G. Ko, I.H. Ali and R. Salghi, "Exploring the Feasibility of New Eco-Friendly Heterocyclic Compounds for Establishing Efficient Corrosion Protection for N80 Steel in a Simulated Oil Well Acidizing Environment: From Molecular-Level Prediction to Experimental Validation," *Colloids Surf. A*, 2023, 656, 130372. doi: 10.1016/j.colsurfa.2022.130372

[9] B.D.B. Tiu and R.C. Advincula, "Polymeric Corrosion Inhibitors for the Oil and Gas Industry: Design Principles and Mechanism," *React. Funct. Polym.*, 2015, 95, 25–45. doi: 10.1016/j.reactfunctpolym.2015.08.006.

[10] A.H. Alamri, "Localized Corrosion and Mitigation Approach of Steel Materials Used in Oil and Gas Pipelines – An Overview," *Eng. Failure Anal.*, 2020, 116, 104735. doi: 10.1016/j.engfailanal.2020.104735

[11] D.S. Chauhan, M.A.J. Mazumder, M.A. Quraishi and K.R. Ansari, "Chitosan-Cinnamaldehyde Schiff Base: A Bioinspired Macromolecule as Corrosion Inhibitor for Oil and Gas Industry," *Int. J. Biol. Macromol.*, 2020, 158, 127–138. doi: 10.1016/j.ijbiomac.2020.04.200

[12] S. Şafak, B. Duran, A. Yurt and G. Türkoğlu, "Schiff Bases as Corrosion Inhibitor for Aluminium in HCl Solution," *Corros. Sci.*, 2012, 54, 251–259. doi: 10.1016/j.corsci.2011.09.026

[13] F.E.-T. Heakal and A.E. Elkholy, "Gemini Surfactants as Corrosion Inhibitors for Carbon Steel," *J. Mol. Liq.*, 2017, 230, 395–407. doi: 10.1016/j.molliq.2017.01.047

[14] M. Farsak, H. Keleş and M.A. Keleş, "New Corrosion Inhibitor for Protection of Low Carbon Steel in HCl Solution," *Corros. Sci.*, 2015, 98, 223–232. doi: 10.1016/j.corsci.2015.05.036

[15] Alamiery, W.N.R.W. Isahak, H.S.S. Aljibori, H.A. Al-Asadi and A.A.H. Kadhum, "Effect of the structure, immersion time and temperature on the corrosion inhibition of 4-pyrrol-1-yl-n-(2,5-dimethyl-pyrrol-1-yl)benzoylamine in 1.0 M HCl solution," *Int. J. Corros. Scale Inhib.*, 2021, 10, no. 2, 700–713. doi: 10.17675/2305-6894-2021-10-2-14

[16] S. Al-Baghdadi, F. Hashim, A. Salam, T. Abed, T. Gaaz, A. Al-Amiery, A.H. Kadhum, K. Reda and W. Ahmed, "Synthesis and corrosion inhibition application of NATN on mild steel surface in acidic media complemented with DFT studies," *Results Phys.*, 2018, 8, 1178–1184. doi: 10.1016/j.rinp.2018.02.007

[17] W.K. Al-Azzawi, A.J. Al Adily, F.F. Sayyid, R.K. Al-Azzawi, M.H. Kzar, H.N. Jawoosh, A.A. Al-Amiery, A.A.H. Kadhum, W.N.R.W. Isahak and M.S. Takriff, "Evaluation of corrosion inhibition characteristics of an N-propionanilide derivative for mild steel in 1 M HCl: Gravimetrical and computational studies," *Int. J. Corros. Scale Inhib.*, 2022, 11, no. 3, 1100–1114. doi: 10.17675/2305-6894-2022-11-3-12

[18] A. Mustafa, F. Sayyid, N. Betti, M. Hanoon, A. Al-Amiery, A. Kadhum and M. Takriff, "Inhibition Evaluation of 5-(4-(1H-pyrrol-1-yl)phenyl)-2-mercapto-1,3,4-oxadiazole for the Corrosion of Mild Steel in an Acid environment: Thermodynamic and DFT Aspects," *Tribologia*, 2021, 38, 39–47. doi: 10.30678/fjt.105330

[19] Y.M. Abdulsahib, A.J.M. Eltmimi, S.A. Alhabeeb, M.M. Hanoon, A.A. Al-Amiery, T. Allami and A.A.H. Kadhum, "Experimental and theoretical investigations on the inhibition efficiency of N-(2,4-dihydroxytolueneylidene)-4-methylpyridin-2-amine for the corrosion of mild steel in hydrochloric acid," *Int. J. Corros. Scale Inhib.*, 2021, 10, no. 3, 885–899. doi: 10.17675/2305-6894-2021-10-3-3

[20] A.K. Khudhair, A.M. Mustafa, M.M. Hanoon, A. Al-Amiery, L.M. Shaker, T. Gazz, A.B. Mohamad, A.H. Kadhum and M.S. Takriff, "Experimental and Theoretical Investigation on the Corrosion Inhibitor Potential of N-MEH for Mild Steel in HCl," *Prog. Color, Color. Coat.*, 2022, 15, 111–122. doi: 10.30509/PCCC.2021.166815.1111

[21] D.S. Zinad, R.D. Salim, N. Betti, L.M. Shaker and A.A. AL-Amiery, "Comparative Investigations of the Corrosion Inhibition Efficiency of a 1-phenyl-2-(1-phenylethylidene)hydrazine and its Analog Against Mild Steel Corrosion in Hydrochloric

Acid Solution," *Prog. Color, Color. Coat.*, 2022, 15, 53–63. doi: 10.30509/pccc.2021.166786.1108

[22] R.D. Salim, N. Betti, M. Hanoon and A.A. Al-Amiery, "2-(2,4-Dimethoxybenzylidene)-N-Phenylhydrazinecarbothioamide as an Efficient Corrosion Inhibitor for Mild Steel in Acidic Environment," *Prog. Color, Color. Coat.*, 2021, 15, 45–52. doi: 10.30509/pccc.2021.166775.1105

[23] A.A. Al-Amiery, L.M. Shaker, A.H. Kadhum and M.S. Takriff, "Exploration of furan derivative for application as a corrosion inhibitor for mild steel in hydrochloric acid solution: Effect of immersion time and temperature on efficiency," *Mater. Today: Proc.*, 2021, 42, 2968–2973. doi: 10.1016/j.matpr.2020.12.807

[24] A.M. Resen, M.M. Hanoon, W.K. Alani, A. Kadhim, A.A. Mohammed, T.S. Gaaz, A.A.H. Kadhum, A.A. Al-Amiery and M.S. Takriff, "Exploration of 8-piperazine-1-ylmethylumbelliferone for application as a corrosion inhibitor for mild steel in hydrochloric acid solution," *Int. J. Corros. Scale Inhib.*, 2021, 10, no. 1, 368–387. doi: 10.17675/2305-6894-2021-10-1-21

[25] M.M. Hanoon, A.M. Resen, A.A. Al-Amiery, A.A.H. Kadhum and M.S. Takriff, "Theoretical and Experimental Studies on the Corrosion Inhibition Potentials of 2-((6-Methyl-2-Ketoquinolin-3-yl)Methylene) Hydrazinecarbothioamide for Mild Steel in 1 M HCl," *Prog. Color, Color. Coat.*, 2021, 15, 21–33. doi: 10.30509/PCCC.2020.166739.1095

[26] F.G. Hashim, T.A. Salman, S.B. Al-Baghdadi, T. Gaaz and A.A. Al-Amiery, "Inhibition effect of hydrazine-derived coumarin on a mild steel surface in hydrochloric acid," *Tribologia*, 2020, 37, 45–53. doi: 10.30678/fjt.95510

[27] A. Alamiery, L.M. Shaker, T. Allami, A.H. Kadhum and M.S. Takriff, "A study of acidic corrosion behavior of Furan-Derived Schiff base for mild steel in hydrochloric acid environment: Experimental, and surface investigation," *Mater. Today: Proc.*, 2021, 44, 2337–2341. doi: 10.1016/j.matpr.2020.12.431

[28] S. Al-Baghdadi, A. Al-Amiery, T. Gaaz and A. Kadhum, "Terephthalohydrazide and isophthalo-hydrazide as new corrosion inhibitors for mild steel in hydrochloric acid: Experimental and theoretical approaches," *Koroze Ochr. Mater.*, 2021, 65, 12–22. doi: 10.2478/kom-2021-0002

[29] M.M. Hanoon, A.M. Resen, L.M. Shaker, A. Kadhum and A. Al-Amiery, "Corrosion investigation of mild steel in aqueous hydrochloric acid environment using n-(Naphthalen-1yl)-1-(4-pyridinyl)methanimine complemented with antibacterial studies," *Biointerface Res. Appl. Chem.*, 2021, 11, 9735–9743. doi: 10.33263/BRIAC112.97359743

[30] S. Al-Baghdadi, T.S. Gaaz, A. Al-Adili, A. Al-Amiery and M. Takriff, "Experimental studies on corrosion inhibition performance of acetylthiophene thiosemicarbazone for mild steel in HCl complemented with DFT investigation," *Int. J. Low-Carbon Technol.*, 2021, 16, 181–188. doi: 10.1093/ijlct/ctaa050

[31] A. Al-Amiery, "Anti-corrosion performance of 2-isonicotinoyl-nphenylhydrazinecarbothioamide for mild steel hydrochloric acid solution: Insights from experimental measurements and quantum chemical calculations," *Surf. Rev. Lett.*, 2021, 28, 2050058. doi: 10.1142/S0218625X20500584

[32] A.A. Alamiery, "Investigations on the corrosion inhibitory effect of newly quinoline derivative on mild steel in HCl solution complemented with antibacterial studies," *Biointerface Res. Appl. Chem.*, 2022, 12, 1561–1568. doi: 10.33263/BRIAC122.15611568

[33] A. Alamiery, "Short report of mild steel corrosion in 0.5 M H2SO4 by 4-ethyl-1-(4-oxo4-phenylbutanoyl)thiosemicarbazide," *Tribologi*, 2021, 30, 90–99.

[34] A.A. Alamiery, W.N.R.W. Isahak and M.S. Takriff, "Inhibition of mild steel corrosion by 4-benzyl-1-(4-oxo-4-phenylbutanoyl)thiosemicarbazide: Gravimetrical, adsorption and theoretical studies," *Lubricants*, 2021, 9, 93. doi: 10.3390/lubricants9090093

[35] M.A. Dawood, Z.M.K. Alasady, M.S. Abdulazeez, D.S. Ahmed, G.M. Sulaiman, A.A.H. Kadhum, L.M. Shaker and A.A. Alamiery, "The corrosion inhibition effect of a pyridine derivative for low carbon steel in 1 M HCl medium: Complemented with antibacterial studies," *Int. J. Corros. Scale Inhib.*, 2021, 10, 1766–1782. doi: 10.17675/2305-6894-2021-10-4-25

[36] A. Alamiery, "Corrosion inhibition effect of 2-N-phenylamino-5-(3-phenyl-3-oxo-1-propyl)-1,3,4-oxadiazole on mild steel in 1 M hydrochloric acid medium: Insight from gravimetric and DFT investigations," *Mater. Sci. Energy Technol.*, 2021, 4, 398–406. doi: 10.1016/j.mset.2021.09.002

[37] A. Alamiery, "Anticorrosion effect of thiosemicarbazide derivative on mild steel in 1 M hydrochloric acid and 0.5 M sulfuric Acid: Gravimetrical and theoretical studies," *Mater. Sci. Energy Technol.*, 2021, 4, 263–273. doi: 10.1016/j.mset.2021.07.004

[38] A. Alamiery, W.N.R.W. Isahak, H. Aljibori, H. Al-Asadi and A. Kadhum, "Effect of the structure, immersion

time and temperature on the corrosion inhibition of 4-pyrrol-1-yln-(2,5-dimethyl-pyrrol-1-yl)benzoylamine in 1.0 m HCl solution," *Int. J. Corros. Scale Inhib.*, 2021, 10, 700–713. doi: 10.17675/2305-6894-2021-10-2-14

[39] C. Bannwarth, E. Caldeweyher, S. Ehlert, A. Hansen, P. Pracht, J. Seibert, S. Spicher and S. Grimme, "Extended tight-binding Quantum Chemistry Methods," *WIREs Comput. Mol. Sci.*, 2021, 11, 2. doi: 10.1002/wcms.1493

[40] H. Chermette, "Chemical Reactivity Indexes in Density Functional Theory," *J. Comput. Chem.*, 1999, 20, no. 1, 129–154. doi: 10.1002/(SICI)1096-987X(19990115)20:13.0.CO;2-A

[41] R. G. Parr and P. K. Chattaraj, "Principle of Maximum Hardness," *J. Am. Chem. Soc.*, vol. 113, no. 5, pp. 1854–1855, 1991. [Online]. Available: doi: 10.1021/ja00005a072

[42] R. P. Iczkowski and J. L. Margrave, "Electronegativity," *J. Am. Chem. Soc.*, vol. 83, no. 17, pp. 3547–3551, 1961. [Online]. Available: doi: 10.1021/ja01478a001

[43] T. Koopmans, "Über die Zuordnung von Wellenfunktionen und Eigenwerten zu den Einzelnen Elektronen Eines Atoms," *Physica*, vol. 1, no. 3, pp. 104–113, 1934. [Online]. Available: doi: 10.1016/S0031-8914(34)90011-2

[44] R. G. Parr, L. V. Szentpály, and S. Liu, "Electrophilicity Index," *J. Am. Chem. Soc.*, vol. 121, no. 9, pp. 1922–1924, 1999. [Online]. Available: doi: 10.1021/ja983494x

[45] N. P. Andreeva, Yu. I. Kuznetsov, and Kh. S. Shikhaliev, "The use of ellipsometry for studying adsorption of organic corrosion inhibitors from aqueous solutions on metals. Review. Part 1. Methods for obtaining adsorption isotherms," *Int. J. Corros. Scale Inhib.*, vol. 11, no. 4, pp. 1716–1723, 2022. [Online]. Available: doi: 10.17675/2305-6894-2022-11-4-20

[46] Yu. I. Kuznetsov, "Organic corrosion inhibitors: where are we now? A review. Part I. Adsorption," *Int. J. Corros. Scale Inhib.*, vol. 4, no. 4, pp. 284–310, 2015. [Online]. Available: doi: 10.17675/2305-6894-2015-4-4-1

[47] Ya. G. Bober, Yu. I. Kuznetsov, and N. P. Andreeva, "Adsorption at Iron and Passivation Effect of Anions of Substituted Phenylanthranilic Acids," *Prot. Met.*, vol. 44, no. 1, pp. 84–90, 2008. [Online]. Available: doi: 10.1134/S0033173208010116

[48] Yu. I. Kuznetsov et al., "Joint adsorption of oleic and phenylanthranilic acids at passive iron," *Prot. Met.*, vol. 39, no. 5, pp. 462–467, 2003. [Online]. Available: doi: 10.1023/A:1025898803486

[49] Yu. I. Kuznetsov et al., "On co-adsorption on passive iron from aqueous 1,2,3-benzotriazole and sodium phenylundecanoate," *Russ. J. Electrochem.*, vol. 46, no. 5, pp. 560–564, 2010. [Online]. Available: doi: 10.1134/S1023193510050101

[50] K. Fukui, "Role of Frontier Orbitals in Chemical Reactions," *Science*, vol. 218, no. 4574, pp. 747–754, 1982. [Online]. Available: doi: 10.1126/science.218.4574.747

[51] M. S. Abdulazeez et al., "Corrosion inhibition of low carbon steel in HCl medium using a thiadiazole derivative: weight loss, DFT studies and antibacterial studies," *Int. J. Corros. Scale Inhib.*, vol. 10, pp. 1812–1828, 2021. [Online]. Available: doi: 10.17675/2305-6894-2021-10-4-27

[52] A. Z. Salman et al., "Selected BISThiadiazole: Synthesis and Corrosion Inhibition Studies on Mild Steel in HCL Environment," *Surf. Rev. Lett.*, vol. 27, p. 2050014, 2020. [Online]. Available: doi: 10.1142/S0218625X20500146

[53] S. Varvara et al., "Evaluation of Some NonToxic Thiadiazole Derivatives as Bronze Corrosion Inhibitors in Aqueous Solution," *Corros. Sci.*, vol. 50, no. 9, pp. 2596–2604, 2008. [Online]. Available: doi: 10.1016/j.corsci.2008.06.046

[54] H. Ibraheem et al., "4-Thiadiazole: The Biological Activities," *Sys. Rev. Pharm.*, vol. 9, no. 1, pp. 36–40, 2018. [Online]. Available: doi: 10.5530/srp.2018.1.7

[55] A. Al-Amiery et al., "Green Antioxidants: Synthesis and Scavenging Activity of Coumarin Thiadiazoles as Potential Antioxidants Complemented by Molecular Modeling Studies," *Free Radicals Antioxid.*, vol. 6, no. 2, pp. 173–177, 2016. [Online]. Available: doi: 10.5530/fra.2016.2.7

[56] R. G. Parr and R. G. Pearson, "Absolute Hardness: Companion Parameter to Absolute Electronegativity," *J. Am. Chem. Soc.*, vol. 105, no. 26, pp. 7512–7516, 1983. [Online]. Available: doi: 10.1021/ja00364a005

[57] T. K. Chaitra et al., "Thermodynamic, Electrochemical and Quantum Chemical Evaluation of Some Triazole Schiff Bases as Mild Steel Corrosion Inhibitors in Acid Media," *J. Mol. Liq.*, vol. 211, pp. 1026–1038, 2015. [Online]. Available: doi: 10.1016/j.molliq.2015.08.031

[58] L. A. Khamaza, "Generalized Diagram of the Ultimate Nominal Stresses (Endurance Limit) and the Corresponding Dimensions of the Non-Propagating Fatigue Cracks for Sharp and Blunt Notches," *Strength Mater.*, vol. 51, no. 3, pp. 350–

360, 2019. [Online]. Available: doi: 10.1007/s11223-019-00081-w

[59] Yu. G. Matvienko, "Approaches of Fracture Mechanics in the Analysis of Admissible Defects in the Form of Notches," *Strength Mater.*, vol. 42, no. 1, pp. 58–63, 2010. [Online]. Available: doi: 10.1007/s11223-010-9188-2

[60] D. Dwivedi et al., "Carbon steel corrosion: a review of key surface properties and characterization methods," *RSC Adv.*, vol. 7, pp. 4580–4610, 2017. [Online]. Available: doi: 10.1039/C6RA25094G

[61] D. A. Winkler, "Predicting the performance of organic corrosion inhibitors," *Metals*, vol. 7, no. 12, p. 553, 2017. [Online]. Available: doi: 10.3390/met7120553

[62] C. Verma, L. O. Olasunkanmi, E. E. Ebenso, and M. A. Quraishi, "Substituents effect on corrosion inhibition performance of organic compounds in aggressive ionic solutions: a review," *J. Mol. Liq.*, vol. 251, pp. 100–118, 2018. [Online]. Available: doi: 10.1016/j.molliq.2017.12.055

[63] O. Kaczerewska et al., "Heteroatoms and π electrons as favorable factors for efficient corrosion protection," *Mater. Corros.*, vol. 70, pp. 1099–1110, 2019. [Online]. Available: doi: 10.1002/maco.201810570

[64] D. K. Verma, Y. Dewangan, A. K. Dewangan, and A. Asatker, "Heteroatom-Based Compounds as Sustainable Corrosion Inhibitors: An Overview," *J. Bio Tribo Corrosion*, vol. 7, pp. 1–18, 2021. [Online]. Available: doi: 10.1007/s40735-020-00447-7

[65] M. Athar, H. Ali, and M. A. Quraishi, "Corrosion inhibition of carbon steel in hydrochloric acid by organic compounds containing heteroatoms," *Br. Corros. J.*, vol. 37, pp. 155–158, 2002. [Online]. Available: doi: 10.1179/000705902225002376

[66] S. Hadisaputra et al., "(E)-ethyl 3-(4-methoxyphenyl) acrylate as corrosion inhibitor of iron in 1 M HCl solutions," *Int. J. Corros. Scale Inhib.*, vol. 7, no. 4, pp. 633–647, 2018. [Online]. Available: doi: 10.17675/2305-6894-2018-7-4-10

[67] S. Hadisaputra et al., "(2R)-5-hydroxy-7-methoxy-2-phenyl-2,3-dihydrochromen-4-one as corrosion inhibitor for Iron in Hydrochloric Acid," *Int. J. Electrochem. Sci.*, vol. 14, pp. 11110–11121, 2019. [Online]. Available: doi: 10.20964/2019.12.77

[68] S. Hadisaputra et al., "Pinostrobin as Copper Corrosion Inhibitor at 1 M H2SO4 Medium," *IOP Conf. Ser. Mater. Sci. Eng.*, vol. 833, p. 012010, 2020. [Online]. Available: doi: 10.1088/1757-899X/833/1/012010

[69] E. S. Ameh, S. C. Ikpeseni, and L. S. Lawal, "A review of field corrosion control and monitoring techniques of the upstream oil and gas pipelines," Nigerian Journal of Technological Development, vol. 14, no. 2, p. 67, Jan. 2018, doi: 10.4314/njtd.v14i2.5.

[70] S. Hadisaputra et al., "Theoretical study of the substituent effect on corrosion inhibition performance of benzimidazole and its derivatives," *Int. J. Corros. Scale Inhib.*, vol. 8, no. 3, pp. 673–688, 2019. [Online]. Available: doi: 10.17675/2305-6894-2019-8-3-15

[71] K. Cao, W. Li, and L. Yu, "Investigation of 1-Phenyl-3-Methyl-5-Pyrazolone as a corrosion inhibitor for mild steel in 1 M hydrochloric acid," *Int. J. Electrochem. Sci.*, vol. 7, pp. 806–818, 2012.

[72] Y. Zhang et al., "Corrosion Inhibition of Carbon Steel by 1-Phenyl-3-Amino-5-Pyrazolone in H2SO4 solution," *Int. J. Electrochem. Sci.*, vol. 14, pp. 999–1008, 2019. [Online]. Available: doi: 10.20964/2019.01.69

[73] A. S. Fouda, A. A. Al-Sarawy, and E. E. El-Katori, "Pyrazolone derivatives as corrosion inhibitors for C-steel in hydrochloric acid solution," *Desalination*, vol. 201, pp. 1–13, 2006. [Online]. Available: doi: 10.1016/j.desal.2006.03.519

[74] S. Hadisaputra et al., "ab initio MP2 and DFT studies of ethyl-p-methoxycinnamate and its derivatives as corrosion inhibitors of iron in acidic medium," *J. Phys.: Conf. Ser.*, vol. 1402, p. 055046, 2019. [Online]. Available: doi: 10.1088/1742-6596/1402/5/055046

[75] V. S. Sastri and J. R. Perumareddi, "Molecular orbital theoretical studies of some organic corrosion inhibitors," *Corros. Sci.*, vol. 53, no. 8, pp. 617–622, 1997. [Online]. Available: doi: 10.5006/1.3290294

[76] G. F. de Sousa et al., "Synthesis, spectroscopic studies and X-ray Crystal structures of new pyrazoline and pyrazole derivatives," *J. Chem. Crystallogr.*, vol. 41, pp. 401–408, 2011. [Online]. Available: doi: 10.1007/s10870-010-9896-2

[77] S. Hadisaputra, Z. Iskandar, and D. Asnawati, "Prediction of the Corrosion Inhibition Efficiency of Imidazole Derivatives: A Quantum Chemical Study," *Acta Chim. Asiana*, vol. 2, no. 1, pp. 88–94, 2019. [Online]. Available: doi: 10.29303/aca.v2i1.15

[78] N. O. Eddy, S. R. Stoyanov, and E. E. Ebenso, "Fluoroquinolones as corrosion inhibitors for mild steel in acidic medium; experimental and

theoretical studies," *Int. J. Electrochem. Sci.*, vol. 5, pp. 1127–1150, 2010.

[79] Y. Wirayani, M. Ulfa, and Y. Yahmin, "Corrosion inhibition efficiency of nicotine based on quantum chemical study," *Acta Chim. Asiana*, vol. 1, no. 2, pp. 37–42, 2018. [Online]. Available: doi: 10.29303/aca.v1i2.29

[80] A. S. Fouda, M. A. Ismail, A. S. Abousalem, and G. Y. Elewady, "Experimental and theoretical studies on corrosion inhibition of 4-amidinophenyl-2,2'-bifuran and its analogues in acidic media," *RSC Adv.*, vol. 7, pp. 46414–46430, 2017. [Online]. Available: doi: 10.1039/C7RA08092A

[81] ASTM International, "Standard Practice for Preparing, Cleaning, and Evaluating Corrosion Test," 2011, pp. 1–9.

[82] G. R. Monama et al., "Hierarchical 4-tetranitro copper (II) phthalocyanine based metal organic framework hybrid composite with improved electrocatalytic efficiency towards hydrogen evolution reaction," *Results Phys.*, vol. 15, p. 102564, 2019. [Online]. Available: doi: 10.1016/j.rinp.2019.102564

[83] M. Tourabi et al., "Electrochemical and XPS studies of the corrosion inhibition of carbon steel in hydrochloric acid pickling solutions by 3,5-bis(2-thienylmethyl)-4-amino-1,2,4-triazole," *Corros. Sci.*, vol. 75, pp. 123–133, 2013. [Online]. Available: doi: 10.1016/j.corsci.2013.05.023

[84] U. M. Eduok, S. A. Umoren, and A. P. Udoh, "Synergistic inhibition effects between leaves and stem extracts of Sida acuta and iodide ion for mild steel corrosion in 1 M H2SO4 solutions," *Arabian J. Chem.*, vol. 5, pp. 325–337, 2012.

[85] B. D. Mert et al., "Experimental and theoretical investigation of 3-amino-1,2,4-triazole-5-thiol as a corrosion inhibitor for carbon steel in HCl medium," *Corros. Sci.*, vol. 53, no. 12, pp. 4265–4272, 2011. [Online]. Available: doi: 10.1016/j.corsci.2011.08.038

[86] NACE International, "Laboratory Corrosion Testing of Metals in Static Chemical Cleaning Solutions at Temperatures below 93°C (200°F)," TM0193-2016-SG, 2000.

[87] A. Alamiery et al., "Corrosion inhibition of low-carbon steel in hydrochloric acid environment using a Schiff base derived from pyrrole: gravimetric and computational studies," *Int. J. Corros. Scale Inhib.*, vol. 10, pp. 749–765, 2021. [Online]. Available: doi: 10.17675/2305-6894-2021-10-2-17

[88] K. M. Manamela et al., "Adsorptive and DFT studies of some imidazolium based ionic liquids as corrosion inhibitors for zinc in acidic medium," *Int. J. Electrochem. Sci.*, vol. 9, pp. 3029–3046, 2014.

[89] N. S. Abtan et al., "Unlocking the Power of 4-Acetamidoantipyrine: A Promising Corrosion Inhibitor for Preserving Mild Steel in Harsh Hydrochloric Acid Environments", *Prog Color Colorants Coat.*, vol. 17, pp. 85-96, 2024. [Online]. Available: doi: 10.30509/pccc.2023.167147.1223

[90] T. Koopmans, "Ordering of wave functions and eigen-energies to the individual electrons of an atom," *Physica*, vol. 1, no. 1–6, pp. 104–113, 1934. [Online]. Available: doi: 10.1016/S0031-8914(34)90011-2

[91] A. J. M. Eltmimi et al., "Inhibitive effects of a novel efficient Schiff base on mild steel in hydrochloric acid environment," *Int. J. Corros. Scale Inhib.*, vol. 10, pp. 634–648, 2021. [Online]. Available: doi: 10.17675/2305-6894-2021-10-2-10

[92] A. Singh et al., "Eco-Friendly Disposal of Expired Anti-Tuberculosis Drug Isoniazid and Its Role in the Protection of Metal," *J. Environ. Chem. Eng.*, vol. 7, p. 102971, 2019. [Online]. Available: doi: 10.1016/j.jece.2019.102971

[93] M. Benabdellah et al., "Thermodynamic, Chemical and Electrochemical Investigations of 2-Mercapto Benzimidazole as Corrosion Inhibitor for Mild Steel in Hydrochloric Acid Solutions," *Arabian J. Chem.*, vol. 4, pp. 17–24, 2011. [Online]. Available: doi: 10.1016/j.arabjc.2010.06.010

[94] R. Haldhar et al., "Valeriana Wallichii Root Extract as a Green & Sustainable Corrosion Inhibitor for Mild Steel in Acidic Environments: Experimental and Theoretical," *Mater. Chem. Front.*, vol. 2, pp. 1225–1237, 2018. [Online]. Available: doi: 10.1039/C8QM00120K

[95] A. K. Singh et al., "Cefacetrile as Corrosion Inhibitor for Mild Steel in Acidic Media," *Int. J. Electrochem. Sci.*, vol. 6, pp. 5689–5700, 2011.

[96] S. Al-Bghdadi et al., "Benzylidene as Efficient Corrosion Inhibition of Mild Steel in Acidic Solution," *Proceedings*, 2019, p. 27. [Online]. Available: doi: 10.3390/ecsoc-23-06472

[97] B. S. Mahdi et al., "Gravimetric analysis and quantum chemical assessment of 4-aminoantipyrine derivatives as corrosion inhibitors," *Int. J. Corros. Scale Inhib.*, vol. 11, no. 3, pp. 1191–1213, 2022. [Online]. Available: doi: 10.17675/2305-6894-2022-11-3-17

[98] A. A. Alamiery, "Study of Corrosion Behavior of N´-(2-(2-oxomethylpyrrol-1-yl) ethyl) piperidine for Mild Steel in the Acid

Environment," *Biointerface Res. Appl. Chem.*, vol. 12, pp. 3638–3646, 2022. [Online]. Available: doi: 10.33263/BRIAC123.36383646

[99] A. Alamiery et al., "Comparative data on corrosion protection of mild steel in HCl using two new thiazoles," *Data Brief*, vol. 40, p. 107838, 2022. [Online]. Available: doi: 10.1016/j.dib.2022.107838

[100] A. M. Mustafa et al., "Inhibition of mild steel corrosion in hydrochloric acid environment by 1-amino-2-mercapto-5-(4-(pyrrol-1-yl)phenyl)-1,3,4-triazole," *S. Afr. J. Chem. Eng.*, vol. 39, pp. 42–51, 2022. [Online]. Available: doi: 10.1016/j.sajce.2021.11.009

[101] W. K. Al-Azzawi et al., "Adsorption and theoretical investigations of a Schiff base for corrosion inhibition of mild steel in an acidic environment," *Int. J. Corros. Scale Inhib.*, vol. 11, no. 3, pp. 1063–1082, 2022. [Online]. Available: doi: 10.17675/2305-6894-2022-11-3-10

[102] D. M. Jamil et al., "Carbethoxythiazole corrosion inhibitor: as an experimentally model and DFT theory," *J. Eng. Appl. Sci.*, vol. 13, pp. 3952–3959, 2018. [Online]. Available: doi: 10.3923/JEASCI.2018.3952.3959

[103] A. Alobaidy et al., "Eco-friendly corrosion inhibitor: experimental studies on the corrosion inhibition performance of creatinine for mild steel in HCl complemented with quantum chemical calculations," *Int. J. Electrochem. Sci.*, vol. 10, pp. 3961–3972, 2015. [Online]. Available: doi: 10.1016/S1452-3981(23)06594-X

[104] A. Al-Amiery et al., "Synthesis, characterization and gravimetric studies of novel triazole-based compound," *Int. J. LowCarbon Technol.*, vol. 15, no. 2, pp. 164–170, 2020. [Online]. Available: doi: 10.1093/ijlct/ctz067

[105] S. Junaedi et al., "Synthesis and characterization of novel corrosion inhibitor derived from oleic acid: 2-Amino-5- Oleyl 1,3,4-Thiadiazol (AOT)," *Int. J. Electrochem. Sci.*, vol. 7, pp. 3543–3554, 2012. [Online]. Available: doi: 10.1016/S1452-3981(23)13976-9

[106] Q. Li et al., "Long-term corrosion monitoring of carbon steels and environmental correlation analysis via the random forest method," *Npj Materials Degradation*, vol. 6, no. 1, Jan. 2022, doi: 10.1038/s41529-021-00211-3.

[107] J. Orlikowski, A. Jażdżewska, I. Łuksa, M. Szociński, and K. Darowicki, "Corrosion Monitoring in Petroleum Installations—Practical Analysis of the Methods," *Materials*, vol. 17, no. 11, p. 2663, Jun. 2024, doi: 10.3390/ma17112663.

[108] A. Al-Amiery et al., "Synthesis, Antimicrobial And Antioxidant Activities of 5-((2-Oxo-2h-Chromen-7- Yloxy)Methyl)-1,3,4-Thiadiazol-2(3h)One Derived From Umbelliferone," *Chem. Nat. Compd.*, vol. 48, pp. 950–954, 2013. [Online]. Available: doi: 10.1007/s10600-013-0436-0

[109] I. Annon et al., "Corrosion inhibition of mild steel in hydrochloric acid environment using thiadiazole derivative: Weight loss, thermodynamics, adsorption and computational investigations," *S. Afr. J. Chem. Eng.*, vol. 41, pp. 244–252, 2022. [Online]. Available: doi: 10.1016/j.sajce.2022.06.011

[110] H. S. Aljibori et al., "The use of a Schiff base derivative to inhibit mild steel corrosion in 1 M HCl solution: a comparison of practical and theoretical findings," *Int. J. Corros. Scale Inhib.*, vol. 11, no. 4, pp. 1435–1455, 2022. [Online]. Available: doi: 10.17675/2305-6894-2022-11-4-2

[111] H. S. Aljibori et al., "Recent progresses in thiadiazole derivatives as corrosion inhibitors in hydrochloric acid solution," *Int. J. Corros. Scale Inhib.*, vol. 12, no. 3, pp. 842–866, 2023. [Online]. Available: doi: 10.17675/2305-6894-2023-12-3-3

[112] L. M. Shaker et al., "Corrosion in solar cells: challenges and solutions for enhanced performance and durability," *J. Opt.*, 2023. [Online]. Available: doi: 10.1007/s12596-023-01277-9

[113] A. L. Jembere et al., "Effect of low calcination temperature on the corrosion inhibition performance of biomass-based Na2SiO3 on mild steel immersed in tap water," *Cogent Engineering*, vol. 10, no. 1, pp. 1-21, 2023. [Online]. Available: doi: 10.1080/23311916.2023.2165631

[114] M. Taha Mohamed et al., "Revolutionizing Corrosion Defense: Unlocking the Power of Expired BCAA", Prog Color Colorants Coat., vol. 17, no. 2, pp. 97-111, 2024. [Online]. Available: doi: 10.30509/pccc.2023. 167156. 1228

[115] M. K. Abbass et al., "Evaluation of 2-Dimethylaminopropionamidoantipyrine as a Corrosion Inhibitor for Mild Steel in HCl Solution: A Combined Experimental and Theoretical Study", *Prog Color Colorants Coat.*, vol. 17, no. 1, pp. 1-10, 2024. [Online]. Available: doi: 10.30509/pccc.2023.167081.1197.

[116] K.Z. Abdulsada et al., " Unleashing the power of polymer surfactants: novel corrosion inhibitors for mild steel in hydrochloric acid," *Int. J. Corros. Scale Inhib.,* vol. 12, no. 4, pp. 2198-2020, 2023. [Online]. Available: doi: 10.17675/2305-6894-2023-12-4-40

[117] H.S. Aljibori et al., "Advances in corrosion protection coatings: A comprehensive review," *Int. J. Corros. Scale Inhib.,* vol. 12, no. 4, pp. 1476-1520, 2023. [Online]. Available: doi: 10.17675/2305-6894-2023-12-4-6.

[118] Y.K. Al-Majedy et al., "Exploring chromone derivatives as environmentally friendly corrosion inhibitors for mild steel in acidic environments: A comprehensive experimental and DFT study," *Int. J. Corros. Scale Inhib.,* vol. 12, no. 3, pp. 1028-1051, 2023. [Online]. Available: doi: 10.17675/2305-6894-2023-12-3-14.

[119] A. Mohammed et al., "Investigation of the Corrosion Inhibition Properties of 4-Cyclohexyl-3-Thiosemicarbazide on Mild Steel in 1 M HCl Solution*", Prog. Color Colorants Coat.,* vol. 16, pp. 347-3592023. [Online]. Available: doi: 10.30509/pccc.2023.167126.1212

[120] W.B. Wan Nik et al., "Piper betle extract as an eco-friendly corrosion inhibitor for aluminium alloy in hydrochloric acid media," *Int. J. Corros. Scale Inhib.,* vol. 12, no. 3, 948-960, 2023. doi: 10.17675/2305-6894-2023-12-3-9.